

R W Building Consultants, Inc.

Consulting and Engineering Services for the Building Industry

P.O. Box 230 Valrico, FL 33595 Phone 813.659.9197

Florida Board of Professional Engineers Certificate of Authorization No. 9813

June 11, 2014

Joseph Zammit
Fleetwood Window and Doors
1 Fleetwood Way
Corona, CA 92879

REF: Non-Impact Glazing Comparative Analysis for Fleetwood Glacier Sliding Glass Door
(Corresponding Test Reports: TEL 01991013, TEL 01991014)

Joseph,

Attached is the non-impact glazing comparative analysis for the above mentioned product.

Included are:

1. A summary chart identifying the tested glazing details, the corresponding non-impact comparable glazing and the ASTM E1300 calculated load resistance. For the sliding glass doors, the non-impact glazing considered is 3/16" tempered insulated glass.
2. A drawing identifying the tested impact glazing and the comparable non-impact glazing details. For example, if the tested impact unit is the "A" glazing, then the non-impact units is "A1".
3. The ASTM E1300 calculations for each tested impact glazing and the comparable non-impact glazing details.

Please contact me if any additional information is required.

Sincerely,

A handwritten signature in black ink, appearing to read 'L F Schmidt'.

Lyndon F. Schmidt, P.E.
Florida PE No. 43409
V.P. Engineering
R.W. Building Consultants, Inc.

FLEETWOOD GLAZING COMPARATIVE ANALYSIS

Glacier 3300 Sliding Glass Door


Test Reports: TEL 01991013, TEL 01991014

		DLO (in.)	ASTM E1300 LOAD RESISTANCE (psf)
TESTED GLAZING	A	55 x 113	69.0
COMPARABLE GLAZING	A1	55 x 113	145


TESTED GLAZING	B	55 x 113	67.8
COMPARABLE GLAZING	B1	55 x 113	145

TESTED IMPACT GLAZING

TEST REPORTS: TEL 01991013; TEL 01991014




A GLAZING DETAIL




B GLAZING DETAIL

NON-IMPACT GLAZING

VERIFIED PER ASTM E1300



A1 GLAZING DETAIL



B1 GLAZING DETAIL

PRODUCT: FLEETWOOD GLACIER 3300		PART OR ASSEMBLY: GLAZING DETAILS	
			BY
			REVISIONS
		NO.	DATE
 RW BUILDING CONSULTANTS, INC. 813.659.9197			
DATE: 6/09/14			
SCALE: N.T.S.			
DWG. BY: JK			
CHK. BY: LFS			
DRAWING NO.: NA			
SHEET <u>1</u> OF <u>1</u>			

Glass Load Resistance Report -- FLEETWOOD NON-IMPACT GLASS COMPARISON

Glazing Information

Edge Supports: 4 Sides
Glazing Angle: 90°
Lite Dimensions:
Width: 55.0 in.
Height: 113 in.

Project Details

Project Name: FLEETWOOD NON-IMPACT GLASS COMPARISON
Location: PF 1666
Comments: TESTED IMPACT GLASS
"A" GLAZING

Glass Construction (Rectangular)

Double Glazed Insulating Unit
Outboard Lite: { Fully Tempered }
Nominal Thickness: 1/4 in.

Air Space: 0.5 in.
Inboard Lite: { Annealed }
Interlayer Type: SentryGlas® Plus
Outboard Ply Thickness: 3/16 in.
Interlayer Thickness: 0.09 in.
Inboard Ply Thickness: 3/16 in.
Nominal Thickness: 3/8 in.

Short Load Duration, Resistance, and Deflection Data

Load (~ 3 sec.): 50.0 psf
Load Resistance: 69.0 psf
Approximate center of glass deflection: 0.49 in.

Conclusion

Based on your design information, the load resistance is greater than or equal to the specified loading.

Statement of Compliance

Procedures followed in determining the resistance of this window glass are in accordance with ASTM E1300-04.

Disclaimer:

This software can be used to determine the load resistance of specified glass types exposed to uniform lateral loads of short or long duration subject to the following conditions:

- The glass is free of edge and surface damage and has been properly glazed in the opening in conformance with the manufacturer's recommendations.
 - Procedures exist to determine load resistance for rectangular glass assemblies that are:
 - a. Continuously supported along all four edges,
 - b. Continuously supported along three edges,
 - c. Continuously supported along two parallel edges, and
 - d. Continuously supported along one edge.
 - The software user has the responsibility of selecting the correct procedures for the required application from the software.
 - The stiffness of members supporting any glass edge shall be sufficient that under design load, edge deflections shall not exceed $L/175$, where L denotes that length of the supported edge.
 - The manufacturer states that the Safety Plus II 0.090 Polyurethane Large Missile Resistant interlayer is comparable to the PVB interlayer.
 - The non-factored load values for laminated glass are representative of test data and calculations performed for an interlayer at a temperature of 50° C (122° F).
- For other limiting conditions that may apply, refer to Section 5 of ASTM E1300 and local building codes.

Neither SDG nor GANA guarantees and each disclaims any responsibility for any particular results relating to the use of the Window Glass Design 2004 Software Program. SDG and GANA disclaim any liability for any personal injury or any loss or damage of any kind, including all indirect, special, or consequential damages and lost profits, arising out of or relating to the use of the Window Glass Design 2004 Software Program.

Prepared by:  on 6/5/2014
LFS

Glass Load Resistance Report -- FLEETWOOD NON-IMPACT GLASS COMPARISON

Glazing Information

Edge Supports: 4 Sides
Glazing Angle: 90°
Lite Dimensions:
Width: 55.0 in.
Height: 113 in.

Project Details

Project Name: FLEETWOOD NON-IMPACT GLASS COMPARISON
Location: PF 1666
Comments: NON-IMPACT COMPARABLE GLASS
3/16" TEMPERED "A1" GLAZING

Glass Construction (Rectangular)

Double Glazed Insulating Unit	Air Space: 0.5 in.
Outboard Lite: { Fully Tempered }	Inboard Lite: { Fully Tempered }
Nominal Thickness: 3/16 in.	Nominal Thickness: 3/16 in.

Short Load Duration, Resistance, and Deflection Data

Load (~ 3 sec.):	50.0 psf
Load Resistance:	145 psf
Approximate center of glass deflection:	1.15 in.

Conclusion

Based on your design information, the load resistance is greater than or equal to the specified loading.

Statement of Compliance

Procedures followed in determining the resistance of this window glass are in accordance with ASTM E1300-04.


Disclaimer:

This software can be used to determine the load resistance of specified glass types exposed to uniform lateral loads of short or long duration subject to the following conditions:

- The glass is free of edge and surface damage and has been properly glazed in the opening in conformance with the manufacturer's recommendations.
- Procedures exist to determine load resistance for rectangular glass assemblies that are:
 - a. Continuously supported along all four edges,
 - b. Continuously supported along three edges,
 - c. Continuously supported along two parallel edges, and
 - d. Continuously supported along one edge.
- The software user has the responsibility of selecting the correct procedures for the required application from the software.
- The stiffness of members supporting any glass edge shall be sufficient that under design load, edge deflections shall not exceed $L/175$, where L denotes that length of the supported edge.
- The manufacturer states that the Safety Plus II 0.090 Polyurethane Large Missile Resistant interlayer is comparable to the PVB interlayer.

For other limiting conditions that may apply, refer to Section 5 of ASTM E1300 and local building codes.

Neither SDG nor GANA guarantees and each disclaims any responsibility for any particular results relating to the use of the Window Glass Design 2004 Software Program. SDG and GANA disclaim any liability for any personal injury or any loss or damage of any kind, including all indirect, special, or consequential damages and lost profits, arising out of or relating to the use of the Window Glass Design 2004 Software Program.

Prepared by:  on 6/11/2014
LFS

Glass Load Resistance Report -- FLEETWOOD NON-IMPACT GLASS COMPARISON

Glazing Information

Edge Supports: 4 Sides
Glazing Angle: 90°
Lite Dimensions:
Width: 55.0 in.
Height: 113 in.

Project Details

Project Name: FLEETWOOD NON-IMPACT GLASS COMPARISON
Location: PF 1666
Comments: TESTED IMPACT GLASS
"B" GLAZING

Glass Construction (Rectangular)

Single Glazed Lite { Annealed }
Interlayer Type: SentryGlas® Plus
Outboard Ply Thickness: 1/4 in.
Interlayer Thickness: 0.09 in.
Inboard Ply Thickness: 1/4 in.
Nominal Thickness: 1/2 in.

Short Load Duration, Resistance, and Deflection Data

Load (~ 3 sec.): 50.0 psf
Load Resistance: 67.8 psf
Approximate center of glass deflection: 0.44 in.

Conclusion

Based on your design information, the load resistance is greater than or equal to the specified loading.

Statement of Compliance

Procedures followed in determining the resistance of this window glass are in accordance with ASTM E1300-04.

Disclaimer:

This software can be used to determine the load resistance of specified glass types exposed to uniform lateral loads of short or long duration subject to the following conditions:

- The glass is free of edge and surface damage and has been properly glazed in the opening in conformance with the manufacturer's recommendations.
- Procedures exist to determine load resistance for rectangular glass assemblies that are:
 - a. Continuously supported along all four edges,
 - b. Continuously supported along three edges,
 - c. Continuously supported along two parallel edges, and
 - d. Continuously supported along one edge.
- The software user has the responsibility of selecting the correct procedures for the required application from the software.
- The stiffness of members supporting any glass edge shall be sufficient that under design load, edge deflections shall not exceed $L/175$, where L denotes that length of the supported edge.
- The manufacturer states that the Safety Plus II 0.090 Polyurethane Large Missile Resistant interlayer is comparable to the PVB interlayer.
- The non-factored load values for laminated glass are representative of test data and calculations performed for an interlayer at a temperature of 50° C (122° F).

For other limiting conditions that may apply, refer to Section 5 of ASTM E1300 and local building codes.

Neither SDG nor GANA guarantees and each disclaims any responsibility for any particular results relating to the use of the Window Glass Design 2004 Software Program. SDG and GANA disclaim any liability for any personal injury or any loss or damage of any kind, including all indirect, special, or consequential damages and lost profits, arising out of or relating to the use of the Window Glass Design 2004 Software Program.

Prepared by: LFS on 6/11/2014

